

FABRICATION TIPS FOR CORIAN® SOLID SURFACE

INTRODUCTION

In commercial and residential environments, Corian® Solid Surface can be used to create unique, fascinating and timeless design statements through numerous applications. Available in a wide variety of chromatic options and patterns, Corian® Solid Surface is used where attractive aesthetics, design flexibility, durability, hygiene and cleanability are high priorities.

This bulletin provides useful fabrication tips in table form to aid in the choice of fabrication methods and settings for downturn edge build-ups, splashbacks, thermoforming and shape integration for the Australian portfolio of Corian® Solid Surface.

REGIONAL AUSTRALIAN COLOUR PORTFOLIO/FABRICATION TIPS

COLOUR		PROPERTIES						FABRICATION					
Name	Code	Heavily pigmented	Veins	Linear	Metallic	Translucent	Kitchen & heavy use applications	Downturn	Splashback	Thermoforming Temperature	Thermoforming Min. internal Radius for 12mm	Shape Integration Standard	Shape Integration Fabricated
Antarctica	ANT						✓	B-C	D-E-F-G	145-165°C	>150 mm	H-I	J
Arrowroot	ARR		✓				✓	B(2)-C(2)	D-E(2)-F-G	145-150°C	>150 mm	H-I	J
Artista Beige	ART	✓	✓					B(2)-C(2)	D-E(2)-F-G	145-150°C	>150mm	H-I	N/A
Artista Canvas	ARC		✓				✓	B(2)-C(2)	D-E(2)-F-G	145-150°C	>150mm	H-I	J
Artista Dust	ARD	✓	✓					B(2)-C(2)	D-E(2)-F-G	145-150°C	>150mm	H-I	N/A
Artista Grey	ARG		✓				✓	B(2)-C(2)	D-E(2)-F-G	145-150°C	>150mm	H-I	J
Artista Mist	ARM	✓	✓					B(2)-C(2)	D-E(2)-F-G	145-150°C	>150mm	H-I	N/A
Artista Sage	ARA		✓				✓	B(2)-C(2)	D-E(2)-F-G	145-150°C	>150mm	H-I	J
Ash Aggregate	ASA	✓	✓					B(2)-C(2)	D-E(2)-F-G	145-150°C	>150 mm	H-I	N/A
Ash Concrete	ASC	✓	✓					B(2)-C(2)	D-E(2)-F-G	145-165°C	>150mm	H-I	N/A
Aspen	ASP						✓	A-B-C	D-E-F-G	145-150°C	>150 mm	H-I	J
Bisque	BIS						✓	A-B-C	D-E-F-G	145-165°C	>50 mm	H-I	J
Calacatta Greige	CLG		✓				✓	B-C	D-F-G	145-165°C	>75mm	I	J
Cameo White	CAW						✓	A-B-C	D-E-F-G	145-165°C	>50 mm	H-I(1)	J
Canvas	CNV						✓	A-B-C	D-E-F-G	145-165°C	>100 mm	H-I	J
Carbon Aggregate	CAA	✓	✓				✓	B-C	D-E-F-G	145-150°C	>150 mm	H-I	J

COLOUR		PROPERTIES						FABRICATION					
Name	Code	Heavily pigmented	Veins	Linear	Metallic	Translucent	Kitchen & heavy use applications	Downturn	Splashback	Thermoforming Temperature	Thermoforming Min. internal Radius for 12mm	Shape Integration Standard	Shape Integration Fabricated
Carbon Concrete	CAC	✓	✓					B-C	D-E-F-G	145-165°C	>75mm	H-I	N/A
Carrara Crema	CCR		✓				✓	B-C	D-F	145-150°C	>150mm	H-I	J
Carrara Lino	CAL		✓				✓	B-C	D-F	145-150°C	>150mm	H-I	J
Cirrus White	CIW		✓		✓		✓	B-C	D-F	145-150°C	>75mm	H-I	J
Clam Shell	CLS		✓				✓	B-C	D-E-F-G	145-150°C	>150 mm	H-I	J
Concrete	CON						✓	A-B-C	D-E-F-G	145-165°C	>75 mm	H-I	J
Cosmos Prima	COP	✓	✓				✓	B-C	D-E-F-G	145-150°C	>75mm	H-I	J
Deep Anthracite	DAN	✓			✓			B-C	D-F-G	145-165°C	>75mm	H-I	N/A
Deep Cloud	DEC	✓						A-B-C	D-E-F-G	145-165°C	>75mm	H-I	N/A
Deep Night Sky	DNS	✓					✓	A-B-C	D-E-F-G	150°C	>75 mm	H-I	J
Deep Nocturne	DEN	✓						A-B-C	D-E-F-G	145-165°C	>75mm	H-I	N/A
Deep Titanium	DET	✓						B-C	D-F	145-165°C	>75mm	H-I	N/A
Designer White	DEW						✓	A-B-C	D-E-F-G	145-165°C	>50 mm	H-I(1)	J
Domino Terrazzo	DOT						✓	B-C	D-F-G	145-150°C	>150 mm	I	J
Dove	DOV						✓	A-B-C	D-E-F-G	145-165°C	>75 mm	H-I	J
Dune Prima	DUP		✓				✓	B(2)-C(2)	D-E(2)-F-G	145-150°C	>150 mm	H-I	J
Elegant Grey	ELG						✓	A-B-C	D-E-F-G	145-165°C	>75 mm	H-I	J
Evening Prima	EVP	✓	✓		✓			B-C	D-F-G	145-165°C	>75mm	H-I	N/A
Everest	EVE						✓	B-C	D-E-F-G	145-165°C	>75 mm	H-I	J
Excavage	EXC						✓	A-B-C	D-E-F-G	145-150°C	>150 mm	H-I	J
Glacier Ice	GLI					✓		A-B-C	D-E-F-G	140-165°C	>50mm	H-I	N/A
Glacier White	GLW						✓	A-B-C	D-E-F-G	145-165°C	>50 mm	H-I(1)	J
Grey Onyx	GRO		✓			✓	✓	B(2)-C(2)	D-E(2)(3)-F-G	145-150°C	>50 mm	H-I	J
Laguna	LAG	✓						A-B-C	D-E-F-G	145-165°C	>150mm	H-I	N/A
Laguna Terrazzo	LAT						✓	B-C	D-F-G	145-150°C	>150 mm	I	J
Lava Rock	LAR	✓	✓				✓	B(2)-C(2)	D-E(2)-F-G	145-150°C	>150 mm	H-I	J
Limestone Prima	LIP		✓				✓	B(2)-C(2)	D-E(2)-F-G	145-150°C	>150 mm	H-I	J
Linen	LIN						✓	A-B-C	D-E-F-G	145-165°C	>50 mm	H-I	J
Natural Grey	NAG	✓	✓		✓			B-C	D-F-G	145-165°C	>75 mm	H-I	N/A
Neutral Aggregate	NEA		✓					B(2)-C(2)	D-E(2)-F-G	145-150°C	>150mm	H-I	N/A
Neutral Concrete	NEC		✓				✓	B-C	D-E-F-G	145-165°C	>75 mm	H-I	J
Pearl Grey	PEG						✓	A-B-C	D-E-F-G	145-165°C	>50 mm	H-I	J
Pebble Terrazzo	PET							B-C	D-F-G	145-150°C	>150 mm	I	J
Platinum	PLA						✓	A-B-C	D-E-F-G	145-165°C	>75 mm	H-I	N/A

COLOUR		PROPERTIES						FABRICATION					
Name	Code	Heavily pigmented	Veins	Linear	Metallic	Translucent	Kitchen & heavy use applications	Downturn	Splashback	Thermoforming Temperature	Thermoforming Min. internal Radius for 12mm	Shape Integration Standard	Shape Integration Fabricated
Rain Cloud	RAC		✓				✓	B(2)-C(2)	D-E(2)-F-G	145-150°C	>150 mm	H-I	J
Rice Paper	RIP						✓	A-B-C	D-E-F-G	145-165°C	>75 mm	H-I	J
River Pearl	RIE		✓	✓		✓	✓	B-C	D-E-F-G	145-150°C	>75 mm	H-I	J
Sagebrush	SAB		✓				✓	B(2)-C(2)	D-E(2)-F-G	145-150°C	>150 mm	H-I	J
Salt	SAL					✓	✓	A-B-C	D-E-F-G	145-165°C	>75 mm	H-I	J
Sand Storm	SAS		✓			✓	✓	A-B(2)-C(2)	D-E(2)-F-G	145-150°C	>150mm	H-I	J
Savannah	SAV						✓	A-B-C	D-E-F-G	145-150°C	>150 mm	H-I	J
Silver Birch	SIB						✓	A-B-C	D-E-F-G	145-165°C	>150 mm	H-I	J
Silver Grey	SIG						✓	A-B-C	D-E-F-G	145-165°C	>50 mm	H-I	J
Smoke Drift Prima	SMP		✓					B-C	D-F-G	145-150°C	>75mm	H-I	N/A
Sparkling Granita	SPG						✓	B-C	D-F	145-165°C	>150mm	H-I	J
Sparkling White	SPW				✓		✓	B-C	D-E-F-G	145-165°C	>75 mm	H-I	J
Stonecrest Smoke	STS		✓				✓	B-C	D-F-G	145-165°C	>50 mm	I	J
Stonique	STO						✓	A-B-C	D-E-F-G	145-150°C	>150 mm	H-I	J
Valente Grigio	VAG		✓			✓	✓	B-C	D-E-F-G	145-150°C	>75 mm	H-I	J
Vanilla	VAN						✓	A-B-C	D-E-F-G	145-165°C	>50 mm	H-I(1)	J
Venaro White	VEW		✓			✓	✓	B-C	D-E-F-G	145-150°C	>75 mm	H-I	J
Verdant	VED	✓						A-B-C	D-E-F-G	145-165°C	>150mm	H-I	N/A
Weathered Aggregate	WEA	✓	✓				✓	B(2)-C(2)	D-E(2)-F-G	145-150°C	>150 mm	H-I	J
Weathered Concrete	WEC	✓	✓					B(2)-C(2)	D-E(2)-F-G	145-165°C	>75mm	H-I	N/A
Whisper	WHS						✓	A-B-C	D-E-F-G	145-165°C	>75 mm	H-I	J
White Jasmine	WHJ						✓	A-B-C	D-E-F-G	145-165°C	>75 mm	H-I	J
White Onyx	WHO		✓			✓	✓	B(2)-C(2)	D-E(2)(3)-F-G	145-150°C	>50 mm	H-I	J
Witch Hazel	WIH		✓				✓	B(2)-C(2)	D-E(2)-F-G	145-150°C	>150 mm	H-I	J

- (1) Deep rebate recommended when using standard shape in the same colour.
(2) Cut and align downturn and upstand details with pre-cut sheet position.
(3) Fabrication E might remove most of the pattern, fabrication F or G is recommended.
(4) Coved splashback only works in the length of the sheet, coved sidesplash does not work.

DOWNTURN



**Options A1 and A2 will provide the same result.*

***Recommended depth of the rebates for option B is 6-8 mm.*

SPLASHBACK



SHAPE INTEGRATION



**Options H1 and H2 will provide the same result.*

***Recommended depth of the rebates for options I and J is 6-8 mm.*

*For options I and J please pay extra care if a drainer area or grooves have to be routed on the worktop:
make sure maximum depth of the drainer grooves are at least 2 mm above the rebate.
Ensure the drainer reinforcement seams tightly to the sink flange beneath the drainer.*

The Corian® Solid Surfaces Australian portfolio shown in this document contains a wide choice of colour options and aesthetics including the options noted in the above table with random veining, linear veining, metallic effects and translucency.

The following technical bulletins provide useful in-depth fabrication guidance for fabricating with these unique and specific Corian® Solid Surface aesthetics:

Corian® Solid Surface Product Fabrication Bulletin: Corian® Solid Surface Directional Aesthetics (K-26833)

Corian® Solid Surface Product Fabrication Bulletin: Veined Aesthetics (K-26828)

Corian® Solid Surface Product Fabrication Bulletin: Metallic and Mica Aesthetics (K-25703)

PLEASE VISIT OUR WEB SITE: WWW.CASF.COM.AU OR CONTACT YOUR CORIAN® REPRESENTATIVE FOR MORE INFORMATION ABOUT CORIAN® SOLID SURFACE.

This information is based on technical data that DuPont de Nemours Inc. and its affiliates ("DuPont") believe to be reliable, and is intended for use by persons having technical skill and at their own discretion and risk. DuPont cannot and does not warrant that this information is absolutely current or accurate, although every effort is made to ensure that it is kept as current and accurate as possible. Because conditions of use are outside DuPont's control, DuPont makes no representations or warranties, express or implied, with respect to the information, or any part thereof, including any warranties of title, non-infringement of copyright or patent rights of others, merchantability, or fitness or suitability for any purpose and assumes no liability or responsibility for the accuracy, completeness, or usefulness of any information. This information should not be relied upon to create specifications, designs, or installation guidelines. The persons responsible for the use and handling of the product are responsible for ensuring the design, fabrication, or installation methods and process present no health or safety hazards. Do not attempt to perform specification, design, fabrication, or installation work without proper training or without the proper personal protection equipment. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents. DuPont shall have no liability for the use of or results obtained from such information, whether or not based on DuPont's negligence. DuPont shall not be liable for (i) any damages, including claims relating to the specification, design, fabrication, installation, or combination of this product with any other product(s), and (ii) special, direct, indirect or consequential damages. DuPont reserves the right to make changes to this information and to this disclaimer. DuPont encourages you to review this information and this disclaimer periodically for any updates or changes. Your continued access or use of this information shall be deemed your acceptance of this disclaimer and any changes and the reasonableness of these standards for notice of changes.

Corian® and the Corian® logo system are registered trademarks or trademarks of affiliates of DuPont de Nemours, Inc. Copyright © 2025 DuPont. All rights reserved.